172 Water-Based Wall Putty

Su Bazlı Duvar Macunu

PRODUCT DESCRIPTION

Water-based putty filling cracks and voids on plastered surfaces, interior and exterior.

AREAS OF USE

Repair and levelling of plaster, gypsum and concrete before painting.

TECHNICAL PROPERTIES

Components	Single-component (1K)
Colour	White
Density (20 °C)	1.75 ± 0.05 kg/L
Volume solids	70% ± 3
Theoretical coverage	1 m²/kg (single coat)
Application method	Spatula, trowel
Thinning	Ready to use, do not thin
Number of coats	Thin layers as required
Equipment cleaning	Water

DRYING TIMES

Sandable	2–4 hours (depending on thickness)
Paintable	24 hours

Values apply at 23 °C ambient temperature and 50% relative humidity; low temperatures and high humidity extend the times.

SURFACE PREPARATION

The surface must be sound, clean, dry and free from dust. Remove blistered or loose paint and dirt; fill cracks and voids with putty and sand smooth. New plaster and concrete must be allowed to cure for at least 28 days.

APPLICATION CONDITIONS

Application and surface temperature: +5 °C to +35 °C. Do not apply in direct sunlight, rain, strong wind or when there is a risk of frost.

PACKAGING

4 kg · 25 kg

STORAGE AND SHELF LIFE

Store in tightly closed original packaging at +5 °C to +35 °C in a cool, dry place. Protect from frost and direct sunlight. In unopened original packaging, from the date of manufacture: 24 months.

HEALTH AND SAFETY

Before use, read the product Safety Data Sheet (SDS) and the hazard and precautionary statements on the label. Ensure adequate ventilation during application; wear suitable protective gloves, goggles and, where necessary, a mask. Keep out of reach of children. Do not empty product residues or containers into drains; dispose of them in accordance with local regulations.

The information in this technical data sheet is based on laboratory tests and practical experience. As application conditions, substrates and equipment are beyond our control, the user must verify the suitability of the product for the intended application. GENAŞ Gen Boya San. ve Tic. A.Ş. is responsible only for the quality of the product and cannot be held liable for uses other than those recommended. This sheet remains valid until superseded; we reserve the right to change product specifications in line with technological developments.