152 Silicone Interior Primer

Silikonlu İç Cephe Astarı

PRODUCT DESCRIPTION

Silicone-based primer for interior surfaces only.

AREAS OF USE

Plaster, gypsum and concrete before interior paints.

TECHNICAL PROPERTIES

Components	Single-component (1K)
Colour	White
Density (20 °C)	1.40 ± 0.05 kg/L
Volume solids	30% ± 3
Theoretical coverage	9 m²/kg (single coat)
Application method	Brush, roller, airless spray
Thinning	10–20% clean water (depending on absorbency)
Number of coats	1 coat
Equipment cleaning	Water

DRYING TIMES

Touch dry	1 hour
Overcoat	4–6 hours

Values apply at 23 °C ambient temperature and 50% relative humidity; low temperatures and high humidity extend the times.

SURFACE PREPARATION

The surface must be sound, clean, dry and free from dust. Remove blistered or loose paint and dirt; fill cracks and voids with putty and sand smooth. New plaster and concrete must be allowed to cure for at least 28 days.

APPLICATION CONDITIONS

Application and surface temperature: +5 °C to +35 °C. Do not apply in direct sunlight, rain, strong wind or when there is a risk of frost.

PACKAGING

3.5 kg · 10 kg · 20 kg

STORAGE AND SHELF LIFE

Store in tightly closed original packaging at +5 °C to +35 °C in a cool, dry place. Protect from frost and direct sunlight. In unopened original packaging, from the date of manufacture: 24 months.

HEALTH AND SAFETY

Before use, read the product Safety Data Sheet (SDS) and the hazard and precautionary statements on the label. Ensure adequate ventilation during application; wear suitable protective gloves, goggles and, where necessary, a mask. Keep out of reach of children. Do not empty product residues or containers into drains; dispose of them in accordance with local regulations.

The information in this technical data sheet is based on laboratory tests and practical experience. As application conditions, substrates and equipment are beyond our control, the user must verify the suitability of the product for the intended application. GENAŞ Gen Boya San. ve Tic. A.Ş. is responsible only for the quality of the product and cannot be held liable for uses other than those recommended. This sheet remains valid until superseded; we reserve the right to change product specifications in line with technological developments.